

伸銅品

# 黄銅 C2801

▶ 比重 8.40



銅(Cu)59~62%、亜鉛(Zn)約40%の配合で、熱間加工が容易で鍛造用に適し、引張強度が高く、展延性があります。黄銅の性質として銅分が57%未満になると硬くて、脆くなるため鋳物として使われております。用途は、打ち抜いたまま又は折り曲げて使用する配線器具部品、ネームプレート、計器板、溶接棒などです。

伸銅品

## 黄銅板



板面(mm)	各種サイズ 板厚(mm)	調質			備考
		1/2H	1/4H	F	
365 × 1,200	0.1		◇		
	0.15		◇		
	0.2		◇		
	0.25		◇		
	0.3		◇		
	0.4		◇		
	0.5		◇		
	0.6		◇		
	0.7		◇		
	0.8		◇	◇	
	1.0		◇	◇	
	1.2		◇	◇	
	1.4			◇	
	1.5		◇	◇	
	1.6			◇	
	1.8			◇	
	2.0		◇	◇	
	2.3			◇	
	2.5			◇	
	2.6			◇	
	3.0			◇	
	3.2			◇	
3.5			◇		
4.0			◇		
4.5			◇		
5.0			◇		
6.0			◇		
8.0			◇		
9.0			◇		
10.0			◇		
12.0			◇		
15.0			◇		
16.0			◇		
20.0			◇		
22.0			◇		

## 黄銅 板

板面(mm)	各種サイズ 板厚(mm)	調質			備考
		1/2H	1/4H	F	
365 × 1,200	25.0		◇		
	30.0		◇		
	35.0			◇	
	40.0			◇	
	45.0			◇	
	50.0			◇	
1,000 × 2,000	0.6		◇		
	0.8		◇		
	1.0		◇		
	1.2		◇		
	1.5		◇		
	1.6		◇		
	2.0		◇		
	2.3		◇		
	2.5		◇		
	3.0		◇		
	3.2		◇		
	4.0		◇		
	5.0		◇		
	6.0		◇		
	8.0		◇		
	10.0		◇		
15.0		◇			
20.0		◇			
1,250 × 2,500	1.0		◇		
	1.2		◇		
	1.5		◇		
	2.0		◇		
	3.0		◇		
切断用	3.0		◇		
	4.0		◇		
	5.0		◇		
	6.0		◇		
	7.0		◇		
	8.0		◇		
	9.0		◇		
	10.0		◇		
	12.0		◇		
	13.0		◇		
	14.0		◇		
	15.0		◇		
	16.0		◇		
	18.0		◇		
	20.0		◇		
	22.0		◇		
25.0		◇			
30.0		◇			
35.0		◇			
40.0		◇			

## 黄銅 板

板 面 (mm)	各種サイズ 板 厚 (mm)	調 質			備 考	
		1/2H	1/4H	F		
切断用	45.0		◇			
	50.0		◇			
	55.0		◇			
	60.0		◇			
	65.0				◇	
	70.0			◇		
	75.0			◇		
	80.0			◇		
	90.0				◇	
	100.0				◇	
	110.0				◇	
	120.0				◇	
	130.0				◇	

◇ 手配品